

Crown Resources



2694 Hayes Wilbanks Road
Toccoa, GA 30577
(864)968-0592

Geotextile Product Description Sheet

Style C039

Asphalt Overlay Fabric

C039 is a asphalt overlay nonwoven fabric produced by needlepunching 100% polypropylene staple fibers in a random network to form a high strength dimensionally stable fabric. The fibers are specially formulated to resist ultraviolet light deterioration, and are inert to commonly encountered soil chemicals. The fabric will not rot or mildew, is non-biodegradable, and is resistant to damage from insects and rodents. C039 conforms to the physical property values listed below:

Fabric Property	Test Method	Units	Minimum Average Roll Value
Grab Tensile	ASTM D 4632	lbs	90 (.40 kN)
Grab Elongation	ASTM D 4632	%	50
Asphalt Retention		gal/sqyd	.2
Melting Point		F (C)	325 (163)
UV Resistance after 500 hrs.	ASTM D 4355	% Strength Retained	70

Packaging	
Roll Dimensions-Foot	12.5/15 x 360
Square Yards Per Roll	500/600
Estimated Roll Weight-Lbs.	135/160

To the best of our knowledge, the information contained herein is accurate. However, Crown Resources cannot anticipate all conditions under which product information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety or suitability of our products either alone or in combination with other products. Final determination of the suitability of any information or material for the use contemplated, of its manner of use, and whether the suggested use infringes any patents is the sole responsibility of the user.